



Scotch®

2221 Electrical Tape

Data Sheet

Product Description

Scotch 2221 Tape provides excellent oil barrier and shows good stress control characteristics. It is a soft, self-fusing, oil resistant, elastomeric PU mastic tape on liner for medium voltage applications.

Applications

Scotch 2221 Tape is designed for oil barrier in oil paper insulated MV cable joints and terminations.

Typical Properties

Property	Typical Value
Colour	Grey
Thickness	1.5mm
Range of temperature	
Continuous operating temp.	90°C
Emergency operating temp.	130°C
Dielectric strength	18kV/mm
Dissipation factor 50 Hz	>0.2
Permittivity 50 Hz	>7.0
Volume resistivity	19 ⁹ Ohm.cm
Shore A Hardness	
(after 15x), 12-24h after compounding	8
Density	1.51%

Note: These are typical values and should not be used for specification purposes.

Installation Technique

The tape shall be applied in half-lapped layers with very little tension to conform and produce a uniform covering. Follow the appropriate instruction drawing for joints or terminations.

Important Notice

Technical information provided by 3M is based on experience and/or tests believed to be reliable, but their accuracy is not guaranteed and the results may not be relevant to every user's application. For this reason 3M does not accept responsibility or liability, direct or consequential, arising from reliance upon any information provided and the user should determine the suitability of the products for their intended use. Nothing in this statement will be deemed to exclude or restrict 3M's liability for death or personal injury arising from its negligence. All questions of liability relating to 3M products are governed by the seller's terms of sale subject where applicable to the prevailing law. If any goods supplied or processed by or on behalf of 3M prove on inspection to be defective in material or workmanship, 3M will (at its option) replace the same or refund to the Buyer the price paid for the goods or services. Except as set out above, all warranties and conditions, whether express or implied, statutory or otherwise are excluded to the fullest extent permissible at law.

3M and Scotch are trademarks of the 3M Company. Printed in the UK.
© 3M United Kingdom PLC, 2003.

Maintenance

Scotch 2221 Tape is stable under normal storage conditions (21°C).

Availability

Scotch 2221 Tape is available from 3M and your local 3M authorised electrical distributor.



Thorne & Derrick
+44 (0) 191 410 4292
www.powerandcables.com